

ATTORNEY'S DOCKET NUMBER

TRANSMITTAL LETTER TO THE UNITED STATES
DESIGNATED/ELECTED OFFICE (DO/EO/US)
CONCERNING A FILING UNDER 35 U.S.C. 371

1511.00002

U.S. APPLICATION NO. (If known, see 37 CFR 1.5)

APPLICATION NO. (If known, see 37 CFR 1.5)
097889130

INTERNATIONAL APPLICATION NO.
PCT/JP00/00160

INTERNATIONAL FILING DATE
14 January 2000

PRIORITY DATE CLAIMED
18 January 1999

TITLE OF INVENTION PESTICIDAL RESIN COMPOSITIONS AND PESTICIDAL PRODUCTS
FORMED FROM THE SAME

APPLICANT(S) FOR DO/EO/US Akira Tabuchi, Kiyozumi Tani, Akiyoshi Inubushi, Atushi Kamada, Masaharu Kamei and Osamu Igarashi

Applicant herewith submits to the United States Designated/Elected Office (DO/EO/US) the following items and other information:

1. ☒ This is a **FIRST** submission of items concerning a filing under 35 U.S.C. 371.
2. ☐ This is a **SECOND** or **SUBSEQUENT** submission of items concerning a filing under 35 U.S.C. 371.
3. ☒ This is an express request to promptly begin national examination procedures (35 U.S.C. 371(f)).
4. ☐ The US has been elected by the expiration of 19 months from the priority date (PCT Article 31).
5. ☒ A copy of the International Application as filed (35 U.S.C. 371(c)(2))
 - a. ☐ is attached hereto (required only if not communicated by the International Bureau).
 - b. ☒ has been communicated by the International Bureau.
 - c. ☐ is not required, as the application was filed in the United States Receiving Office (RO/US).
6. ☒ An English language translation of the International Application as filed (35 U.S.C. 371(c)(2)).
7. ☐ Amendments to the claims of the International Application under PCT Article 19 (35 U.S.C. 371(c)(3))
 - a. ☐ are attached hereto (required only if not communicated by the International Bureau).
 - b. ☐ have been communicated by the International Bureau.
 - c. ☐ have not been made; however, the time limit for making such amendments has NOT expired.
 - d. ☐ have not been made and will not be made.
8. ☐ An English language translation of the amendments to the claims under PCT Article 19 (35 U.S.C. 371(c)(3)).
9. ☐ An oath or declaration of the inventor(s) (35 U.S.C. 371(c)(4)).
10. ☐ An English language translation of the annexes to the International Preliminary Examination Report under PCT Article 36 (35 U.S.C. 371(c)(5)).

Items 11 to 16 below concern document(s) or information included:

11. ☒ An Information Disclosure Statement under 37 CFR 1.97 and 1.98.
12. ☐ An assignment document for recording. A separate cover sheet in compliance with 37 CFR 3.28 and 3.31 is included.
13. ☒ A FIRST preliminary amendment.
☐ A SECOND or SUBSEQUENT preliminary amendment.
14. ☐ A substitute specification.
15. ☐ A change of power of attorney and/or address letter.
16. ☐ Other items or information:
- CERTIFICATE OF MAILING BY "EXPRESS MAIL"**
Express Mail Filing Label Number EL841173475

CERTIFICATE OF MAILING BY "EXPRESS MAIL"

Express Mail Shipping Label Number EL841173475US

Date of Deposit, July 12, 2001

I hereby certify that this paper or fee is being deposited with the United States Postal Service "Express Mail Post Office to Addressee" service under 37 CFR 1.10 on the date indicated above and is addressed to the Assistant Commissioner of Patents, Washington, D. C. 20231.

Karen A. Sanderson

(Typed or Printed Name of Person Mailing Paper or Fee)

Karen A. Sanderson
(Signature of person mailing paper or fee)

U.S. APPLICATION NO. 097/889130		INTERNATIONAL APPLICATION NO. PCT/JP00/00160		ATTORNEY'S DOCKET NUMBER 1511.00002																																																																		
<p>17. <input checked="" type="checkbox"/> The following fees are submitted:</p> <p>BASIC NATIONAL FEE (37 CFR 1.492 (a) (1) - (5)):</p> <p>Neither international preliminary examination fee (37 CFR 1.482) nor international search fee (37 CFR 1.445(a)(2)) paid to USPTO and International Search Report not prepared by the EPO or JPO \$1000.00</p> <p>International preliminary examination fee (37 CFR 1.482) not paid to USPTO but International Search Report prepared by the EPO or JPO \$860.00</p> <p>International preliminary examination fee (37 CFR 1.482) not paid to USPTO but international search fee (37 CFR 1.445(a)(2)) paid to USPTO \$710.00</p> <p>International preliminary examination fee paid to USPTO (37 CFR 1.482) but all claims did not satisfy provisions of PCT Article 33(1)-(4) \$690.00</p> <p>International preliminary examination fee paid to USPTO (37 CFR 1.482) and all claims satisfied provisions of PCT Article 33(1)-(4) \$100.00</p> <p style="text-align: center;">ENTER APPROPRIATE BASIC FEE AMOUNT =</p> <p>Surcharge of \$130.00 for furnishing the oath or declaration later than <input type="checkbox"/> 20 <input type="checkbox"/> 30 months from the earliest claimed priority date (37 CFR 1.492(e)).</p> <table border="1" style="width: 100%; border-collapse: collapse;"> <thead> <tr> <th style="width: 20%;">CLAIMS</th> <th style="width: 20%;">NUMBER FILED</th> <th style="width: 20%;">NUMBER EXTRA</th> <th style="width: 20%;">RATE</th> <th style="width: 20%;"></th> </tr> </thead> <tbody> <tr> <td>Total claims</td> <td>4 - 20 =</td> <td>0</td> <td>X \$18.00</td> <td>\$ 0.00</td> </tr> <tr> <td>Independent claims</td> <td>1 - 3 =</td> <td>0</td> <td>X \$80.00</td> <td>\$ 0.00</td> </tr> <tr> <td colspan="4">MULTIPLE DEPENDENT CLAIM(S) (if applicable)</td> <td>+ \$270.00</td> </tr> <tr> <td colspan="4" style="text-align: right;">TOTAL OF ABOVE CALCULATIONS =</td> <td>\$ 860.00</td> </tr> <tr> <td colspan="4"> <input type="checkbox"/> Applicant claims small entity status. See 37 CFR 1.27. The fees indicated above are reduced by 1/2. </td> <td>\$</td> </tr> <tr> <td colspan="4" style="text-align: right;">SUBTOTAL =</td> <td>\$ 860.00</td> </tr> <tr> <td colspan="4">Processing fee of \$130.00 for furnishing the English translation later than <input type="checkbox"/> 20 <input type="checkbox"/> 30 months from the earliest claimed priority date (37 CFR 1.492(f)).</td> <td>\$</td> </tr> <tr> <td colspan="4" style="text-align: right;">TOTAL NATIONAL FEE =</td> <td>\$ 860.00</td> </tr> <tr> <td colspan="4">Fee for recording the enclosed assignment (37 CFR 1.21(h)). The assignment must be accompanied by an appropriate cover sheet (37 CFR 3.28, 3.31). \$40.00 per property</td> <td>\$</td> </tr> <tr> <td colspan="4" style="text-align: right;">TOTAL FEES ENCLOSED =</td> <td>\$ 860.00</td> </tr> <tr> <td colspan="4"></td> <td>Amount to be refunded: \$</td> </tr> <tr> <td colspan="4"></td> <td>charged: \$</td> </tr> </tbody></table>				CLAIMS	NUMBER FILED	NUMBER EXTRA	RATE		Total claims	4 - 20 =	0	X \$18.00	\$ 0.00	Independent claims	1 - 3 =	0	X \$80.00	\$ 0.00	MULTIPLE DEPENDENT CLAIM(S) (if applicable)				+ \$270.00	TOTAL OF ABOVE CALCULATIONS =				\$ 860.00	<input type="checkbox"/> Applicant claims small entity status. See 37 CFR 1.27. The fees indicated above are reduced by 1/2.				\$	SUBTOTAL =				\$ 860.00	Processing fee of \$130.00 for furnishing the English translation later than <input type="checkbox"/> 20 <input type="checkbox"/> 30 months from the earliest claimed priority date (37 CFR 1.492(f)).				\$	TOTAL NATIONAL FEE =				\$ 860.00	Fee for recording the enclosed assignment (37 CFR 1.21(h)). The assignment must be accompanied by an appropriate cover sheet (37 CFR 3.28, 3.31). \$40.00 per property				\$	TOTAL FEES ENCLOSED =				\$ 860.00					Amount to be refunded: \$					charged: \$	<p>CALCULATIONS</p> <p>PTO USE ONLY</p>	
CLAIMS	NUMBER FILED	NUMBER EXTRA	RATE																																																																			
Total claims	4 - 20 =	0	X \$18.00	\$ 0.00																																																																		
Independent claims	1 - 3 =	0	X \$80.00	\$ 0.00																																																																		
MULTIPLE DEPENDENT CLAIM(S) (if applicable)				+ \$270.00																																																																		
TOTAL OF ABOVE CALCULATIONS =				\$ 860.00																																																																		
<input type="checkbox"/> Applicant claims small entity status. See 37 CFR 1.27. The fees indicated above are reduced by 1/2.				\$																																																																		
SUBTOTAL =				\$ 860.00																																																																		
Processing fee of \$130.00 for furnishing the English translation later than <input type="checkbox"/> 20 <input type="checkbox"/> 30 months from the earliest claimed priority date (37 CFR 1.492(f)).				\$																																																																		
TOTAL NATIONAL FEE =				\$ 860.00																																																																		
Fee for recording the enclosed assignment (37 CFR 1.21(h)). The assignment must be accompanied by an appropriate cover sheet (37 CFR 3.28, 3.31). \$40.00 per property				\$																																																																		
TOTAL FEES ENCLOSED =				\$ 860.00																																																																		
				Amount to be refunded: \$																																																																		
				charged: \$																																																																		

a. ☒ A check in the amount of \$ 860.00 to cover the above fees is enclosed.


b. ☐ Please charge my Deposit Account No. _____ in the amount of \$ _____ to cover the above fees. A duplicate copy of this sheet is enclosed.

c. ☒ The Commissioner is hereby authorized to charge any additional fees which may be required, or credit any overpayment to Deposit Account No. 23-0785. A duplicate copy of this sheet is enclosed.

NOTE: Where an appropriate time limit under 37 CFR 1.494 or 1.495 has not been met, a petition to revive (37 CFR 1.137(a) or (b)) must be filed and granted to restore the application to pending status.

SEND ALL CORRESPONDENCE TO:

Jeffrey L. Clark
Wood, Phillips, VanSanten, Clark & Mortimer
500 West Madison Street, Suite 3800
Chicago, IL 60661-2511
(312) 876-1800


 SIGNATURE: _____
 Jeffrey L. Clark
 NAME: _____
 29,141
 REGISTRATION NUMBER

IN THE UNITED STATES PATENT AND TRADEMARK OFFICE

In re Application of:)
)
AKIRA TABUCHI et al) PESTICIDAL COMPOSITIONS
) AND PESTICIDAL PRODUCTS
Corres. to PCT/JP00/00160) FORMED FROM THE SAME
)
Serial No. (unassigned))
)
Filed (herewith))

PRELIMINARY AMENDMENT

Box PCT
Commissioner for Patents
Washington, D.C. 20231

Sir:

Applicants wish to amend their above-identified application as
follows:

IN THE CLAIMS:

Amended claim 3 is as follows:

3. (Amended) A pesticidal product formed from any one of
the pesticidal resin composition according to claim 1.

CERTIFICATE OF MAILING BY "EXPRESS MAIL"

"Express Mail" mailing label number EL841173475US
Date of Deposit July 12, 2001

I hereby certify that this paper or fee is being deposited with the United States Postal Service "Express Mail Post Office to Addressee" service under 37 CFR 1.10 on the date indicated above and is addressed to the Commissioner for Patents, Washington, D.C. 20231.

Karen A. Sanderson

(Typed or printed name of person mailing paper or fee)

Karen A. Sanderson
(Signature of person mailing paper or fee)

Please add new claim 4 as follows:


--4. A pesticidal product formed from any one of the pesticidal resin composition according to claim 2.--

REMARKS

By this Preliminary Amendment, multiple dependencies have been removed from the claims to place the application in proper U.S. form. Applicants believe the application is now in condition for allowance. Early notification to that effect is respectfully requested.

Respectfully submitted,

WOOD, PHILLIPS, VAN SANTEN,
CLARK & MORTIMER

By _____
Jeffrey L. Clark
Reg. No. 29,141

July 12, 2001

500 West Madison Street
Suite 3800
Chicago, IL 60661-2511
(312) 876-1800

Marked Up Version of Claims

3. (Amended) A pesticidal product formed from any one of the pesticidal resin composition according to [any one of claims] claim 1 [and 2].

DESCRIPTION

PESTICIDAL RESIN COMPOSITIONS AND PESTICIDAL PRODUCTS
FORMED FROM THE SAME

5

Technical Field

The present invention relates to pesticidal resin compositions and pesticidal products formed from the same.

10

Background Art

There exists a problem in that intrusion of insects or the like into electric equipment or transport equipment causes malfunctions or disorders thereof. For example, a TV receiver causes heat inside thereof, which may attract pests such as insects or spiders, which intrude into the inside of the TV receiver through small holes on a rear side thereof, and cause malfunction through short-circuit of a circuit, or the like. Such intrusion of insects or the like causing disorders sometimes occur in computers, telephone switchboards, industrial robots or the like.

15

20

To address the above problem, it is conceivable to prepare a pesticidal substance carried on a resin material used for structural member, exterior member, fluid transferring pipe, drive member or the like of the instruments.

25

As a resin material having a pesticidal property, there have been proposed a soft resin such as a low molecular weight straight-chain polyethylene resin, polypropylene resin or polyvinyl chloride resin that is blended as a matrix resin with an insecticide or the like. These resins are of the type that is capable of holding a large volume of a chemical agent such as an insecticide, but has a drawbacks, namely a poor strength, poor heat resistance and poor chemical resistance. Therefore, a product which is formed by using such a resin

composition itself as a forming material is greatly limited in its application, and therefore is only applicable to such as a cat collar for which little strength is required (see Japanese Patent Application Laid-open Numbers Hei-6-315332, 5-284871, and 6-141724).

5 A so-called engineering plastic has an excellent heat resistance and chemical resistance. However, it usually exhibits a poor capability in carrying the chemical agent mentioned above. As a result, such a plastic mixed with the chemical agent exhibits no sustained release, produces no pesticidal effect or loses the pesticidal effect in a short period of time even if the initial effect can be produced, or poses any other drawbacks.

Summary of the Invention

10 In consideration of the problems with the prior arts, it is an object of the present invention to provide a resin composition that has such a heat resistance and chemical resistance as to enable the resin composition to be used as a structural member or the like, as well as being capable of exhibiting the pesticidal activity for a prolonged period of time.

15 Specifically, according to the present invention, there is provided a pesticidal resin composition that contains (A) at least one resin selected from polyamide resins and polyacetal resins (hereinafter referred simply to "A component" in some cases), (B) at least one compound selected from sulfone amide derivatives, sulfonic acid ester derivatives, phosphoric acid ester derivatives, phosphazene derivatives, carboxylic acid amide derivatives, carboxylic acid ester derivatives (hereinafter referred simply to "B component" in some cases), and (C) a chemical agent having a pesticidal property (hereinafter referred simply to "C component" in some cases).

20 With the pesticidal resin composition containing the above ingredients, it

is possible to obtain a pesticidal product that has such a strength, heat resistance and chemical resistance as to render the product usable as a structural member, as well as being capable of exhibiting the pesticidal activity for a prolonged period of time.

5 According to the present invention, the pesticidal resin composition may be mixed with (D) a fibrous inorganic filler (hereinafter referred simply to "D component"). The composition mixed with the fibrous inorganic filler can preferably achieve more improved sustained release. Also, the mixture of the fibrous inorganic filler is preferable since it contributes to improvement of
10 mechanical property.

 According to the present invention, there is also provided a pesticidal product formed from any one of the pesticidal resin compositions mentioned above. The pesticidal product may be manufactured by forming the pesticidal resin composition directly into a desirable shape, or by extruding the same and forming it
15 temporarily into pellets or the like for storing and distributing. The forming to the pellets enables the shaping of the product by a known method.

Best Mode for Carrying out the Invention

 As specific examples of the polyamide resins in (A) at least one resin
20 selected from polyamide resins and polyacetal resins, it can be cited polyamide resins such as polyamide-6, polyamide-66, polyamide-11, or polyamide-12 resin, and aromatic polyamide resins such as polyamide-MXD or polyamide-6T resin.

 As specific examples of the polyacetal resins, it can be cited a homopolymer comprising oxymethylene unit only, as well as a copolymer comprising
25 oxymethylene unit as a main component and a different copolymer unit such as oxyethylene unit as an accessory component, cross-linked polymer formed by the cross-linkage therebetween or graft copolymer formed by graft copolymerization

therebetween.

It is possible to use, as the A component, solely the one selected from the polyamide resins or the one selected from the polyacetal resins, or the mixture comprising two or more resins selected from these resins.

5 The polyamide resins or polyacetal resins used as the A component in the present invention may be used in the form of alloy with different resins as far as it does not deteriorate the effects produced by the present invention. As specific examples of resins which can be employed as the different resins in this alloy, it can be cited polyethylene, polypropylene, polystyrene, acrylonitrile-butadiene-styrene
10 resin, polyethylene terephthalate, polybutylene terephthalate, polycarbonate, polyarylate, polyphenylene ether, thermoplastic polyurethane, liquid crystal polyester and the like. These may be used as being mixed into the (A) component in an amount of less than 70 weight parts.

15 It is conceivable that at least one compound selected from (B) sulfone amide derivatives, sulfonic acid ester derivatives, carboxylic acid amide derivatives, carboxylic acid ester derivatives can dissolve and hold the (C) component, thus achieving an action enabling the composition to have sustained release.

20 As specific examples of the carboxylic acid ester derivatives among those used as the (B) component, it can be cited an alkyl ester, aromatic ester or the like of various carboxylic acids, for which a hydroxyl group, nitro group, amino group, epoxy group, halogen or the like may be substituted. Particularly, those with the hydroxyl group, epoxy group or the like are preferable for their favorable compatibility with polyamide.

25 As specific examples of the carboxylic acid ester derivatives, it can be cited phthalic acid ester derivatives such as dimethyl phthalate, diethyl phthalate, di-n-octyl-phthalate, diphenyl phthalate, benzyl phthalate, dimethoxy-ethyl-phthalate, 4,5-epoxy-hexahydro-phthalic-acid-di(2-ethyl hexyl), 4,5-epoxy-cyclohexahydro

phthalic acid (7,8-epoxy-2-octenyl), 4,5-epoxy-cyclohexahydro-phthalic acid-di(9,10-epoxyoctadecyl), 4,5-epoxy-cyclohexahydro-phthalic acid-di(10,11-epoxyundecyl), phthalic acid-di(tetrahydrofurfuryloxyethyl), various phthalic acid mixed esters and an ethylene oxide adduct of a phthalic acid mixed ester,

5 isophthalic acid ester derivatives, tetrahydrophthalic acid ester derivatives, benzoic acid ester derivatives such as parahydroxy benzoic acid butoxyethyl, parahydroxy benzoic acid cyclohexyloxy ethoxy ethoxyethyl, parahydroxy benzoic acid 2-ethylhexyl, hydroxybenzoic acid ester of ω -alkyl (oligo) ethylene oxide and a parahydroxy benzoic acid adduct of an undecyl glycidyl ether, propionic acid ester

10 derivatives such as thiodipropionic acid di(tetrahydrofurfuryloxy ethyl), adipic acid ester derivatives, azelaic acid ester derivatives, sebacic acid ester derivatives, dodecane-2-acid ester derivatives, maleic acid ester derivatives, fumaric acid ester derivatives, trioctyl trimellitate ester derivatives, citric acid ester derivatives such as tri(butoxy ethoxyethyl)citrate, di-n-octyl-mono(nonyl phenoxy ethyl)citrate,


15 tri-n-octyl citrate, dioctyl(tetrahydrofurfuryloxy ethyl)citrate, trimyrystyl citrate and triethyl citrate, itaconic acid ester derivatives, oleic acid ester derivatives such as tetrahydrofurfuryl oleate, ricinoleic acid ester derivatives, lactic acid ester derivatives such as (n-butyl)lactate, (2-ethylhexyl)lactate, (n-butoxyethoxyethyl)lactate, (ethoxy-n-octoxyethyl)lactate and (n-decyloxyethoxyethyl)lactate, tartaric acid ester derivatives such as

20 di(ethoxyoctoxyethyl)tartrate and (n-octyl) (nonylphenoxyethyl)tartrate, malic acid ester derivatives such as dibutoxyethyl malate, di(n-butoxyethoxyethyl)malate, distearyl malate and octadecynyl isononyl malate, salicylic acid ester derivatives such as a salicylic acid adduct of an benzyl glycidyl ether.

25 As specific examples of the phosphoric acid ester derivatives, it can be cited trimethyl phosphate, triethyl phosphate, tributyl phosphate, tris(2-ethylhexyl)phosphate, 2-ethylhexyldiphenyl phosphate, tributoxyethyl phosphate,

triphenyl phosphate, crezyldiphenyl phosphate, isodecyldiphenyl phosphate, tricresyl phosphate, trixylenyl phosphate, tri(chloroethyl)phosphate, dimethylphenyl diphenyl phosphate, and tetrakis(2,4 di-tertiary-butylphenyl)4,4'-biphenylen diphosphonate.

- 5 It can be cited, as specific examples of the phosphazene derivatives, cyclic phosphazene compounds having the general formula (1)




- 10 in which

m stands for an integer of 3 to 25,

R¹, R² are equal or different and represent a C₁₋₈-alkyl group and a phenyl group which may be substituted with a C₁₋₈-alkyl group and/or aryl group,

- 15 as well as straight chain phosphazene compounds having the general formula (2)



in which

- 20 n stands for an integer of 3 to 1000,

R³, R⁴ are equal or different and represent a C₁₋₈ alkyl group and a phenyl group which may be substituted with a C₁₋₈ alkyl group and/or aryl group,


X represents a group $\cdot\text{N}=\text{P}(\text{OR}^3)_3$, group $\cdot\text{N}=\text{P}(\text{OR}^4)_3$, group $\cdot\text{N}=\text{P}(\text{O})(\text{OR}^3)$ or group $\cdot\text{N}=\text{P}(\text{O})(\text{OR}^4)$,

- 25 Y represents a group $\cdot\text{P}(\text{OR}^3)_4$, group $\cdot\text{P}(\text{OR}^4)_4$, group $\cdot\text{P}(\text{O})(\text{OR}^3)_2$ or group $\cdot\text{P}(\text{O})(\text{OR}^4)_2$,

as well as at least one phosphazene compound selected from the aforesaid phosphazene compounds

in which

two oxygen atoms resulting from the releasing of alkyl groups or the like from substituents R^1 , R^2 , R^3 , R^4 are linked to each other via at least one crosslinking group selected from the group consisting of o-, m-, p-phenylene group, biphenylene group and groups having the general formula (3)



in which

r represents 0 or 1,

A represents a group: $-\text{SO}_2-$, $-\text{S}-$, $-\text{O}-$, or $-\text{C}(\text{CH}_3)_2-$.

As specific examples of the cyclic phosphazene compounds having the general formula (1), it can be cited hexa-phenoxy-cyclo-triphosphazene, octa-phenoxy-cyclo-tetraphosphazene, deca-phenoxy-cyclo-pentaphosphazene, hexa-propoxy-cyclo-triphosphazene, octa-propoxy-cyclo-tetraphosphazene, and deca-propoxy-cyclo-pentaphosphazene.

As specific examples of the straight chain phosphazene compounds having the general formula (2), it can be cited chain phosphazene compounds each having a chain dichlorphosphazene with which a propoxy group and/or phenoxy group are substituted.

As specific examples of the crosslinking structure having the general formula (3), it can be cited 4,4'-sulfonyldiphenylene(bisphenol-S-residue), 4,4'-oxydiphenylene group, 4,4'-thiodiphenylene group, and 4,4'-diphenylene group.

These phosphazene derivatives each may have a portion or portions which

are substituted with an amino group and/or phenylamino group.

Those phosphazene derivatives each may be solely used, or the mixture of two or more derivatives may be used. Also, the mixture of a cyclic phosphazene and a straight chain phosphazene may be used.

5 As a specific example of the carboxylic acid amide derivatives, it can be cited N-cyclohexyl benzoic acid amide or the like.

As specific examples of the sulfone amide derivatives, it can be cited N-methyl-benzenesulfonamide, N-ethyl-benzenesulfonamide, N-butyl-benzenesulfonamide, N-cyclohexyl-benzenesulfonamide, N-ethyl-P-
10 toluenesulfonamide, N-butyl-toluenesulfonamide, and N-cyclohexyl-toluenesulfonamide.

As a specific example of the sulfonic acid ester derivatives, it can be cited benzene sulfonic acid ethyl or the like.

As the (B) component, one derivative selected from sulfone amide
15 derivatives, sulfonic acid ester derivatives, carboxylic acid amide derivatives and carboxylic acid ester derivatives may be solely used, or a mixture of two or more derivatives selected therefrom may be used.

The (C) chemical agent having a pesticidal property is a chemical agent exhibiting pesticidal activity against various agricultural harmful insects,
20 insanitary insects or pests such as any other insects, spiders, mites or rats. It can be cited as the (C) chemical agent compounds exhibiting a pest repellent activity, compounds exhibiting insecticidal, miticidal, spidercidal, rodenticidal or any other pesticidal activity, compositions exhibiting antifeedant activity, pest growth control activity, and the like.

25 As specific examples of the chemical agent having such a pesticidal property, it can be cited chloronicotinyl insecticides such as imidacloprid insecticide, compounds having silicon atoms such as silafluofen, carbamate compounds such as

benfuracarb, alanicarb, metoxadiazone [5-methoxy-3-(2-methoxyphenyl)-1,3,4-oxadiazole-2(3H)-one], carbosulfan, phenobcarb, carbaryl, methomyl, propoxur and phenoxycarb, pyrethroid compounds such as pyrethrin, allethrin, d1,d-T80-allethrin, d-T80-resmethrin, bioallethrin, d-T80-phthalthrin, phthalthrin, 5 resmethrin, furamethrin, proparthrin, permethrin, acrinathrin, etofenprox, tralomethrin, phenothrin, d-phenothrin, fenvalerate, empenethrin and prarethrin, tefluthrin, organophosphorous compounds such as dichlorovos, fenitrothion, diazinon, malathion, propaphos, fenthion, trichlorforn, naled, temephos, fenclphos, chlorpyriphosmethyl, ciafos, calcrofos, azamethiphos, pyridafenthion, 10 propetamphos and chlorpyriphos, as well as their isomers, derivatives and affinities.

As specific examples of the compounds exhibiting pest growth control activity, it can be cited methoprene, pyriproxyfen, kinoprene, hydroprene, diofenolan, NC-170, flufenoxuron, diflubenzuron, lufenuron and chlorfluazuron.

15 As specific examples of miticides, it can be cited kelthane, chlorfenapyr, tebufenpyrad, pyridaben, milbemectin, and fenpyroximate. As specific examples of rodenticides, it can be cited scilliroside, norbormide, zinc phosphide, thallium sulfate, yellow phosphor, antu, warfarin, coumarine, coumatetralyl, bromadiolone and difethialone.

20 As the (D) fibrous inorganic filler, those having an average fiber diameter of 0.05 to 10 μ m, an average fiber length of 3 to 150 μ m are preferably used, and it can be cited as specific examples thereof potassium 4-titanate fiber, potassium 6-titanate fiber, potassium 8-titanate fiber, titania fiber, monoclinic titania fiber, silica fiber, wollastonite and zonotlite. These may be each solely used or used as 25 mixed with each other. Among these fibrous inorganic fillers, the potassium 8-titanate fiber is most preferable.

The fibrous inorganic filler is preferably mixed into a compound because it

achieves more improved sustained release. Also, the mixture of the fibrous inorganic filler is preferable since it contributes to improvement of mechanical property.

While the fibrous inorganic filler may be used as it is, it may be subjected to surface treatment with a surface treating agent such as a silane coupling agent such as amino silane, epoxy silane and acrylic silane, or a titanate coupling agent.

An inorganic filler such as zeolite may be used together in a resin composition of the present invention to such an extent as not to deteriorate the object of the present invention.

While the mixing proportion of each component in the resin composition of the present invention may be suitably set according to an actually selected component, a usual proportion is such that the (B) component is set within the range of 0.05 and 100 weight parts and preferably 2 and 50 weight parts, and the (C) component is set within the range of 0.01 and 30 weight parts and preferably 0.1 to 20 weight parts with respect to 100 weight parts of the (A) component

Where the (D) component is mixed, its mixing proportion is preferably 2 to 60 weight part with respect to 100 weight parts of the (A) component. When the mixing proportion of the (D) component is more than 60 weight parts, it poses a difficulty in shaping. On the contrary, when the mixing proportion is less than 2 weight parts, a mixing effect of the fibrous inorganic filler may not sufficiently produced.

The pesticidal resin composition of the present invention may be manufactured for example by mixing the respective components together, and then melting and kneading the same. The respective components may be mixed together by dry-blending technique using a tumbler, blender, mixer, etc. Alternatively, the mixing of these components may be made by the feeding of the components through the same hopper or different hoppers of a kneading machine.

The pesticidal resin composition obtained may be directly formed into a desirable shape for use as a pesticidal product, or may be extruded and formed temporarily into pellets or the like for storing and distributing. The reason for forming the composition to the pellets or the like is that they may be processed into a shape by a known method.

For shaping the pesticidal resin composition of the present invention, various known shaping techniques may be employed. For example, injection molding, extrusion molding, press molding, blow molding, or machining technique may be used.

The pesticidal product of the present invention is not necessarily limited to a specific shape. Rather, it may be formed in flat plate, stick, cylinder, comb, sphere, or any shape.

The pesticidal resin composition may be combined with conventional resin compositions, metals or the like, and formed into such as a structural member in two or more than two colors, a desirable part of which structural member exhibiting the pesticidal activity.

EMBODIMENTS

The present invention will be discussed in more detail by illustrating embodiments and comparative examples as below.

Embodiments 1 to 3 and Comparative examples 1 to 4

By using a biaxial extruder of 45 mm ϕ with a resin temperature set at 190 °C, the (A) component (for which polyamide 12, represented by "PA" in the type-indicating fields of the TABLES herein, was used as a polyamide resin) was poured therinto and molten. The polyamide 12 used is marketed under the name "DAIAMID L-1940" and manufactured by DAICEL-HÜLS LTD. The mixture of the (B) component (for which N-butyl-benzenesulfonamide, represented by "A" in

the type-indicating fields of the TABLES herein, was used as a sulfone amide derivative) and the (C) component (for which permethrin, represented by "A" in the type-indicating fields of the TABLES herein, was used as a pesticide) in the proportions stated in the TABLE 1 or 2 was placed into the biaxial extruder through a side hopper thereof with pressure by a plunger pump and formed into pellets. Thus, the resin compositions of the embodiments 1 to 3, and the comparative examples 1 to 4 were obtained.

The molded articles for the testing each having a cylindrical shape with an inner diameter of 15 mm ϕ , thickness of 1.5 mm and length of 40 mm were prepared by an injection molding machine, using the pellets obtained.

However, the resin composition of the comparative example 4 had a chemical agent bled-out on the surfaces of the pellets, so that an injection molded article could not be prepared.

TABLE 1

Embodiments	(A) component		(B) component		(C) component		(D) component		Pesticidal activity		
	Types	Mixed amts.	Types	Mixed amts.	Types	Mixed amts.	Types	Mixed amts.	7 days	3 months	6 months
1	PA	80	A	15	A	5	-	-	○	△	×
2	PA	75	A	15	A	10	-	-	○	○	×
3	PA	65	A	15	A	20	-	-	○	○	×
4	POM	85	A	10	A	5	-	-	○	△	×
5	POM	80	A	10	A	10	-	-	○	△	×
6	POM	70	A	10	A	20	-	-	○	○	△
7	PA	80	A	15	B	5	-	-	○	△	×
8	PA	75	A	15	B	10	-	-	○	△	×
9	PA	65	A	15	B	20	-	-	○	△	△
10	PA	80	B	15	A	5	-	-	○	△	×
11	PA	75	B	15	A	10	-	-	○	△	×
12	PA	65	B	15	A	20	-	-	○	△	△
13	PA	80	C	15	A	5	-	-	○	△	×
14	PA	75	C	15	A	10	-	-	○	△	△
15	PA	65	C	15	A	20	-	-	○	○	△
16	PA	70	A	15	A	5	A	10	○	○	△
17	PA	60	A	15	A	5	A	20	○	○	△
18	PA	65	A	15	A	10	A	10	○	○	○
19	PA	55	A	15	A	10	A	20	○	○	○
20	PA	55	A	15	A	20	A	10	○	○	○
21	PA	45	A	15	A	20	A	20	○	○	○

TABLE 2

Compa- rative exam- ples	(A) component		(B) component		(C) component		(D) component		Pesticidal activity		
	Types	Mixed amts.	Types	Mixed amts.	Types	Mixed amts.	Types	Mixed amts.	7 days	3 months	6 months
1	PA	85	A	15	-	0	-	-	×	-	-
2	PA	95	-	0	A	5	-	-	○	×	-
3	PA	90	-	0	A	10	-	-	○	×	-
4	PA	80	-	0	A	20	-	-	.	.	.
5	POM	90	A	10	-	0	-	-	×	-	-
6	PP	80	-	0	A	20	-	-	-	-	-
7	EVA	80	-	0	A	20	-	-	-	-	--

Embodiments 4 to 6 and Comparative example 5

By using a biaxial extruder of 45 mm ϕ with a resin temperature set at 185 °C, the (A) component (for which polyacetal resin, represented by "POM" in the type-indicating fields of the TABLES herein, was used) was poured thereinto and molten. The polyacetal resin used is marketed under the name "DURACON M90-44" and manufactured by POLYPLASTICS CO., LTD. The mixture of the (B) component (for which N-butyl-benzenesulfonamide was used as a sulfone amide derivative) and the (C) component (for which permethrin was used as a pesticide) in the proportions stated in the TABLES 1 or 2, was placed into the biaxial extruder through a side hopper thereof with pressure by a plunger pump and formed into pellets. Thus, the resin compositions of the embodiments 4 to 6, and the comparative example 5 were obtained.

The molded articles for the testing each having a cylindrical shape with an inner diameter of 15 mm ϕ , thickness of 1.5 mm and length of 40 mm were prepared by an injection molding machine, using the pellets obtained.

Embodiments 7 to 9

The resin compositions of embodiments 7 to 9 were obtained in the same manner as the first embodiment except for the (C) component, for which methoxydiazone (a pesticide represented by "B" in the type-indicating fields of the

TABLES herein) was alternatively used.

Also, the molded articles for the testing each having a cylindrical shape with an inner diameter of 15mm ϕ , thickness of 1.5 mm and length of 40 mm were prepared by an injection molding machine, using the pellets obtained.

5 Embodiments 10 to 12


The resin compositions of embodiments 10 to 12 were obtained in the same manner as the first embodiment except for the (B) component, for which parahydroxybenzoic acid 2 ethylhexyl (a carboxylic acid ester derivative, represented by "B" in the type-indicating fields of the TABLES herein) was
10 alternatively used.

Also, the molded articles for the testing each having a cylindrical shape with an inner diameter of 15 mm ϕ , thickness of 1.5 mm and length of 40 mm were prepared by an injection molding machine, using the pellets obtained.

Embodiments 13 to 15

The resin compositions of embodiments 13 to 15 and the comparative
15 example 8 were obtained in the same manner as the first embodiment except for the (B) component, for which a phosphazene composition, represented by "C" in the type-indicating fields of the TABLES, having the general formula (4) stated below was alternatively used.

Also, the molded articles for the testing each having a cylindrical shape
20 with an inner diameter of 15mm ϕ , thickness of 1.5 mm and length of 40 mm were prepared by an injection molding machine, using the pellets obtained.



Embodiments 16 to 21

By using a biaxial extruder of 45 mm ϕ with a resin temperature set at 190 °C, the (A) component (for which the same polyamide resin embodiment was used) was poured thereto and molten. The polyamide resin used is marketed under the name "DALAMID L-1940". The mixture of the (B) component (for which N-butyl-benzenesulfonamide was used as a sulfone amide derivative) and the (C) component (for which permethrin was used as a pesticide) in the proportions stated in the TABLE 1 was placed into the biaxial extruder through a side hopper thereof with pressure by a plunger pump. Then, the (D) component (for which potassium 8-titanate fiber, represented by "A" in the type-indicating fields of the TABLES herein, having an average fiber diameter of 0.5 μ m and average fiber length of 18 μ m was used as a fibrous inorganic filler) was fed via a side-feed. The potassium 8-titanate fiber used is marketed under the name of "TISMO-D" and manufactured by OTSUKA KAGAKU KABUSHIKI KAISHA.

The resultant was then formed into pellets. Thus, the resin compositions of the embodiments 16 to 21 were obtained.

The molded articles for the testing each having a cylindrical shape with an inner diameter of 15 mm ϕ , thickness of 1.5 mm and length of 40 mm were prepared by an injection molding machine, using the pellets obtained.

Comparative example 6

By using a biaxial extruder of 45 mm ϕ with a resin temperature set at 240 °C, 80 weight parts of polypropylene resin, represented by "PP" for convenience in the type-indicating fields of the (A) component was poured thereto and molten. The polypropylene resin used is marketed under the name of "UBE POLYPRO" and manufactured by UBE INDUSTRIES LTD. 20 weight parts of the (C) component (for which permethrin was used as a pesticide) was placed into the biaxial extruder through a side hopper thereof with pressure by a plunger pump, and then the

resultant was formed into pellets. Thus, the resin composition of the comparative example 6 was obtained.

The molded articles for the testing each having a cylindrical shape with an inner diameter of 15 mm ϕ , thickness of 1.5 mm and length of 40 mm were also prepared for the resin composition of the comparative example 6 by an injection molding machine in the same manner as each embodiment.

Comparative example 7

By using a biaxial extruder of 45 mm ϕ with a resin temperature set at 150 °C, 80 weight parts of ethylene-vinyl acetate resin, represented by "EVA" for convenience in the type-indicating fields of the (A) component in the TABLES, having a vinyl acetate content of 32 % by weight, was poured thereinto and molten. The ethylene-vinyl acetate resin used is marketed under the name of "ULTRASEN 750" and manufactured by TOYO SODA KABUSHIKI KAISHA. 20 weight parts of the (C) component (for which permethrin was used as a pesticide) was placed into the biaxial extruder through a side hopper thereof with pressure by a plunger pump, and then the resultant was formed into pellets. Thus, the resin composition of the comparative example 6 was obtained.

The molded articles for the testing each having a cylindrical shape with an inner diameter of 15 mm ϕ , thickness of 1.5 mm and length of 40 mm were also prepared for the resin composition of the comparative example 7 by an injection molding machine in the same manner as each embodiment.

Test example 1

The molded articles for the testing obtained in the respective embodiments and comparative examples were left in an atmosphere of 25°C. After the elapse of 7 days, three months and 6 months respectively, gauzes, which are manufactured by TORAY INDUSTRIES, INC., and marketed under the name of "TETORON C-119 SKYLARK", were attached to the opposite ends of the molded articles and

prepared five test objects each keeping one spider (*agelena limbata*) therein were prepared for each embodiment and comparative example. The life or death of *agelena limbata* was confirmed in 24 hours.

The life or death of *agelena limbata* was determined by applying stimuli thereto with a pincette. That is, when no reaction has been observed, it has been determined as being dead.

The test results are shown in the TABLES 1 and 2.

The evaluation of the pesticidal activity shown in the TABLES 1 and 2 was made based upon the proportion of the died test objects with respect to all the test objects (i.e., 5 test objects).

In the TABLES, the symbols, \bigcirc , \triangle and \times respectively represent the death rates of the *agelena limbata*, namely not less than 80 %, between 40 to not more than 80 % and not more than 40 %.

Test example 2

Test pieces were prepared by an injection molding technique, using the resin compositions of the embodiments 1 and 4, and the comparative examples 6 and 7, and the tests were conducted to determine the pulling strength (ASTM D638), flexural strength (ASTM D790), heat deflection temperature (ASTM D648, 4.6 kg/cm²) and gasoline resistance.

To evaluate the gasoline resistance, the test pieces each having a cylindrical shape with an inner diameter of 15 mm ϕ , thickness of 1.5 mm, and length of 40 mm were immersed in gasoline (regular gasoline manufactured by IDEMITSU PETROCHEMICAL CO., LTD.) for 24 hours, and then changes of the test pieces in length were measured just after taking the test pieces out of gasoline.

The test results are shown in TABLE 3.

In the TABLE 3, the symbols \bigcirc and \triangle respectively represent the changes of not more than 0.2 % and not less than 0.2 % in length, and \times

represents a molten state.

TABLE 3

	Pulling strength (kgf/cm ²)	Flexural strength (kgf/cm ²)	Heat deflection temperature (°C)	Gasoline resistance
Embodiment 1	370	600	135	○
Embodiment 4	550	800	145	○
Comparative Example 6	330	400	108	△
Comparative example 7	<50	<50	<40	×

5 As is apparent from the test examples 1 and 2, the molded articles of all the respective embodiments exhibit the pesticidal activity. Particularly, the molded article mixed with the fibrous inorganic filler exhibits an excellent sustained release.

10 The molded article of each embodiment has a sufficient strength, heat resistance and the like.

As described above, with the pesticidal resin composition of the present invention, it is possible to obtain a pesticidal product that has such a heat resistance and chemical resistance as to enable the resin composition to be used as a structural member or the like, as well as being capable of exhibiting the pesticidal activity for a prolonged period of time.

CLAIMS

1. A pesticidal resin composition that contains (A) at least one resin selected from polyamide resins and polyacetal resins, (B) at least one compound selected from sulfone amide derivatives, sulfonic acid ester derivatives, phosphoric acid ester derivatives, phosphazene derivatives, carboxylic acid amide derivatives, carboxylic acid ester derivatives, and (C) a chemical agent having a pesticidal property.
2. A pesticidal resin composition according to claim 1, which is mixed with a fibrous inorganic filler.
3. A pesticidal product formed from any one of the pesticidal resin composition according to any one of claims 1 and 2.

ABSTRACT

According to the present invention, there is provided a pesticidal resin composition that contains (A) at least one resin selected from polyamide resins and polyacetal resins, (B) at least one compound selected from sulfone amide derivatives, sulfonic acid ester derivatives, phosphoric acid ester derivatives, phosphazene derivatives, carboxylic acid amide derivatives, carboxylic acid ester derivatives, and (C) a chemical agent having a pesticidal property. With the pesticidal resin composition containing the above ingredients, it is possible to obtain a pesticidal product that has such a strength, heat resistance and chemical resistance as to render the product usable as a structural member, as well as being capable of exhibiting the pesticidal activity for a prolonged period of time.

Declaration and Power of Attorney for Patent Application

特許出願宣言書及び委任状

Japanese Language Declaration

日本語宣言書

私は、以下に記名された発明者として、ここに下記の通り宣言する：

As a below named inventor, I hereby declare that:

私の住所、郵便の宛先そして国籍は、私の氏名の後に記載された通りである。

My residence, post office address and citizenship are as stated next to my name

下記の名称の発明について、特許請求範囲に記載され、且つ特許が求められている発明主題に関して、私は、最初、最先且つ唯一の発明者である（唯一の氏名が記載されている場合）か、或いは最初、最先且つ共同発明者である（複数の氏名が記載されている場合）と信じている。

I believe I am the original, first and sole inventor (if only one name is listed below) or an original, first and joint inventor (if plural names are listed below) of the subject matter which is claimed and for which a patent is sought on the invention entitled

PESTICIDAL RESIN COMPOSITIONS AND

PESTICIDAL PRODUCTS FORMED FROM THE SAME

上記発明の明細書はここに添付されているが、下記の欄がチェックされている場合は、この限りでない：

the specification of which is attached hereto unless the following box is checked:

☒ was filed on January 14, 2000
as United States Application Number or
PCT International Application Number
PCT/JP00/00160 and was amended on
(if applicable)

私は、上記の修正書によって修正された、特許請求範囲を含む上記明細書を検討し、且つ内容を理解していることをここに表明する。

I hereby state that I have reviewed and understand the contents of the above identified specification, including the claims, as amended by any amendment referred to above.

私は、連邦規則法典第37編規則1.56に定義されている、特許性について重要な情報を開示する義務があることを認める。

I acknowledge the duty to disclose information which is material to patentability as defined in Title 37, Code of Federal Regulations, Section 1.56

Burden Hour Statement: This form is estimated to take 0.4 hours to complete. Time will vary depending upon the need of the individual case. Any comments on the amount of time you are required to complete this form should be sent to Chief Information Officer, U.S. Patent and Trademark Office, Washington, DC 20231. DO NOT SEND FEES OR COMPLETED FORMS TO THIS ADDRESS. SEND TO: Commissioner of Patents and Trademarks, Washington, DC 20231

Under the Paperwork Reduction Act of 1995, no persons are required to respond to a collection of information unless it displays a valid OMB control number

PTO/SB/106 (5-00)

Japanese Language Declaration (日本語宣言書)

私は、ここに、以下に記載した外国での特許出願または発明者証の出願、或いは米国以外の少なくとも一國を指定している米国法典第35編第365条(a)によるPCT国際出願について、同第119条(a)(4)項又は第365条(b)項に基づいて優先権を主張するとともに、優先権を主張する本出願の出願日より前の出願日を有する外国での特許出願または発明者証の出願、或いはPCT国際出願については、いかなる出願も、下記の枠内をチェックすることにより示した。

I hereby claim foreign priority under Title 35, United States Code, Section 119(a)-(d) or 365(b) of any foreign application(s) for patent or inventor's certificate, or 365(a) of any PCT International application which designated at least one country other than the United States listed below and have also identified below, by checking the box, any foreign application for patent or inventor's certificate, or PCT International application having a filing date before that of the application for which priority is claimed

Prior Foreign Application(s)
外国での先行出願

Priority Not Claimed
優先権主張なし

11-009743 (Number) (番号)	Japan (Country) (国名)	18/1/1999 (Day/Month/Year Filed) (出願日/月/年)	<input type="checkbox"/>
_____ (Number) (番号)	_____ (Country) (国名)	_____ (Day/Month/Year Filed) (出願日/月/年)	<input type="checkbox"/>

私は、ここに、下記のいかなる米国仮特許出願についても、その米国法典第35編第119条(a)項の利益を主張する。

I hereby claim the benefit under Title 35, United States Code, Section 119(e) of any United States provisional application(s) listed below

_____ (Application No.) (出願番号)	_____ (Filing Date) (出願日)	_____ (Application No.) (出願番号)	_____ (Filing Date) (出願日)
--------------------------------------	---------------------------------	--------------------------------------	---------------------------------

私は、ここに、下記のいかなる米国出願についても、その米国法典第35編第120条に基づく利益を主張し、又米國を指定するいかなるPCT国際出願についても、その同第365条(c)に基づく利益を主張する。また、本出願の各特許請求の範囲の主題が、米国法典第35編第112条第1段に規定された態様で、先行する米国出願又はPCT国際出願に開示されていない場合においては、その先行出願の出願日と本国内出願日またはPCT国際出願日との間の期間中に入手された情報で、連邦規則法典第37編規則1.56に定義された特許性に関わる重要な情報について開示義務があることを承認する。

I hereby claim the benefit under Title 35, United States Code, Section 120 of any United States application(s), or 365(c) of any PCT International application designating the United States, listed below and, insofar as the subject matter of each of the claims of this application is not disclosed in the prior United States or PCT International application in the manner provided by the first paragraph of Title 35, United States Code Section 112, I acknowledge the duty to disclose information which is material to patentability as defined in Title 37, Code of Federal Regulations, Section 1.56 which became available between the filing date of the prior application and the national or PCT International filing date of application.

_____ (Application No.) (出願番号)	_____ (Filing Date) (出願日)	_____ (Status: Patented, Pending, Abandoned) (現況: 特許許可、係属中、放棄)
_____ (Application No.) (出願番号)	_____ (Filing Date) (出願日)	_____ (Status: Patented, Pending, Abandoned) (現況: 特許許可、係属中、放棄)

私は、ここに表明された私自身の知識に係わる陳述が真実であり、且つ情報と信ずることに基づく陳述が、真実であると信じられることを宣言し、さらに、故意に虚偽の陳述などを行った場合は、米国法典第18編第1001条に基づき、罰金または拘禁、若しくはその両方により処罰され、またそのような故意による虚偽の陳述は、本出願またはそれに対して発行されるいかなる特許も、その有効性に問題が生ずることを理解した上で陳述が行われたことを、ここに宣言する。

I hereby declare that all statements made herein of my own knowledge are true and that all statements made on information and belief are believed to be true; and further that these statements were made with the knowledge that willful false statements and the like so made are punishable by fine or imprisonment, or both, under Section 1001 of Title 18 of the United States Code and that such willful false statements may jeopardize the validity of the application or any patent issued thereon.

Japanese Language Declaration

(日本語宣言書)

委任状: 私は本出願を審査する手続を行い、且つ米国特許商標庁との全ての業務を遂行するために、記名された発明者として、下記の弁護士及び/または弁理士を任命する。(氏名及び登録番号を記載すること)

POWER OF ATTORNEY: As a named inventor, I hereby appoint the following attorney(s) and/or agent(s) to prosecute this application and transact all business in the Patent and Trademark Office connected therewith (list name and registration number)

書類送付先

Richard S. Phillips (Reg. No. 17,314),
Wm. A. VanSanten (Reg. No. 22,810),
Jeffrey A. Clark (Reg. No. 29,144), John
S. Mortimer (Reg. No. 30,497), F. William
McLaughlin (Reg. No. 32,273) & Dean A. Monco

Send Correspondence to:

John S. Mortimer, Esq.
Wood, Phillips, VanSanten,
Clark & Mortimer
500 West Madison Street, Suite 3800
Chicago, IL 60661-2511 - USA

直通電話連絡先: (氏名及び電話番号) (Reg. No. 30,091)

Direct Telephone Calls to: (name and telephone number)

John S. Mortimer
(312) 876-1800

唯一または第一発明者氏名

Full name of sole or first inventor

Akira TABUCHI

発明者の署名

日付

Inventor's signature

Date

Akira Tabuchi

23/07/2001

住所

Residence

c/o OTSUKA KAGAKU KABUSHIKI KAISHA, Tokushima Research
Kawauchi-cho, Tokushima-shi, Tokushima 771-0193 Japan

Laboratories, #63, Kagasuno,

国籍

Citizenship

Japanese

郵便の宛先

Post Office Address

Same as the above residence

第二共同発明者がある場合、その氏名

Full name of second joint inventor, if any

Kiyozumi TANI

第二共同発明者の署名

日付

Second inventor's signature

Date

Kiyozumi Tani

23/07/2001

住所

Residence

c/o OTSUKA KAGAKU KABUSHIKI KAISHA, Tokushima Research
Kawauchi-cho, Tokushima-shi, Tokushima 771-0193 Japan

Laboratories, #63, Kagasuno,

国籍

Citizenship

Japanese

郵便の宛先

Post Office Address

Same as the above residence

(第三以下の共同発明者についても同様に記載し、署名をすること)

(Supply similar information and signature for third and subsequent joint inventors.)

Additional Inventor

3-D
Akiyoshi INUBUSHI

(Full name of third joint inventor)

Akiyoshi Inubushi

23/07/2001

(Third inventor's signature)

(Date)

c/o OTSUKA KAGAKU KABUSHIKI KAISHA, Tokushima Research Laboratories, 463, Kagasuno,
Kawauchi-cho, Tokushima-shi, Tokushima 771-0193 Japan JPX

(Residence)

Japanese

(Citizenship)

Same as the above residence

(Post Office Address)

4-D
Atushi KAMADA

(Full name of fourth joint inventor)

Atushi Kamada

23/07/2001

(Fourth inventor's signature)

(Date)

c/o EARTH BIOCHEMICAL CO., LTD., 923, Kagasuno, Kawauchi-cho, Tokushima-shi, Tokushima
771-0130 Japan JPX

(Residence)

Japanese

(Citizenship)

Same as the above residence

(Post Office Address)

Additional Inventor

5-00
Masaharu KAMEI

(Full name of fifth joint inventor)

Masaharu Kamei

23/07/2001

(Fifth inventor's signature)

(Date)

c/o EARTH BIOCHEMICAL CO., LTD., 923, Kagasuno, Kawauchi-cho, Tokushima-shi, Tokushima-

771-0130 Japan JP X

(Residence)

Japanese

(Citizenship)

Same as the above residence

(Post Office Address)

6-00
Osamu IGARASHI

(Full name of sixth joint inventor)

Osamu Igarashi

23/07/2001

(Sixth inventor's signature)

(Date)

c/o NIX, INC., 3-3, Minatomirai 2-chome, Nishi-ku, Yokohama-shi, Kanagawa 220-6108 Japan JP X

(Residence)

Japanese

(Citizenship)

Same as the above residence

(Post Office Address)